

TIN (Sn) BASE		PURE TIN																	HIGH PURITY																	DISC/BLOCK			
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
351-192G	%								0.0007	0.0002		0.0005	0.0007		0.0007																								
SnSb		Sb				Others/Set Only	Size	Type	Form			SnSb			Sb						Others/Set Only	Size	Type	Form															
265-TA1	%	1.03					Ø 40x13mm	RM	Disc			265-TA8		%	8.02							Ø 40x13mm	RM	Disc															
265-TA2	%	2.01					Ø 40x13mm	RM	Disc			265-TA10		%	0.09							Ø 40x13mm	RM	Disc															
265-TA3	%	3.05					Ø 40x13mm	RM	Disc			265-TA12		%	2.42							Ø 40x13mm	RM	Disc															
265-TA5	%	5.09					Ø 40x13mm	RM	Disc																														
						PURE TIN						PIG TIN																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-NF54/1	%	0.005	0.005	0.01		0.002	0.002	0.002	0.01	0.005	0.005	0.002	0.03		0.005			0.0005	R			Y	Ø 40x13mm	RM	Disc														
265-NF54/2	%	0.01	0.01	0.07		0.005	0.005	0.005	0.05	0.01	0.01	0.005	0.15		0.01			0.001	R			Y	Ø 40x13mm	RM	Disc														
265-NF54/3	%	0.03	0.03	0.15		0.01	0.001	0.01	0.15	0.015	0.02	0.01	0.4		0.02			0.003	R			Y	Ø 40x13mm	RM	Disc														
265-NF54/4	%	0.06		0.3		0.02	0.005	0.02	0.3	0.025	0.04	0.02	0.7		0.04			0.007	R			Y	Ø 40x13mm	RM	Disc														
265-NF54/5	%	0.1		0.5		0.035	0.01		0.5		0.08		1		0.08			0.015	R			Y	Ø 40x13mm	RM	Disc														
341-SR1D	%	0.009	0.001	0.003	0.003	0.01	0.007		0.009	0.001	0.015	-0.001	0.03		0.021			0.007	R		Te 0.003	Ø 40x10mm	CRM	Disc															
341-SR2D	%	0.029	0.003	0.041	0.008	0.056	0.041		0.054	0.002	0.049	0.0096	0.127		0.063			0.015	R		Te 0.022	Ø 40x10mm	CRM	Disc															
341-SR3E	%	0.007	0.003	0.061	0.003	0.105	0.022		0.101	0.003	0.029	0.0009	0.29		0.14			0.014	R		Te 0.008	Ø 40x10mm	CRM	Disc															
						TIN ALLOY						SnAg																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-TS3X	%	3		0.01		0.05			0.2				0.02		0.2			0.001	R			Y	Ø 40x13mm	RM	Disc														
265-TS4X	%	4		0.02		0.1			0.1				0.05		0.1			0.0025	R			Y	Ø 40x13mm	RM	Disc														
265-TS5X	%	5		0.05		0.25			0.03				0.1		0.05			0.005	R			Y	Ø 40x13mm	RM	Disc														
						TIN ALLOY						SnSb																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Form															
265-TA4X	%			0.03		0.1	0.015		0.04	0.04			0.1		4			0.015	R			Y	Ø 40x13mm	RM	Disc														
265-TA5X	%			0.02		0.005	<0.005		0.003	0.004			0.025		5				R			Y	Ø 40x13mm	RM	Disc														
265-TA6X	%			0.05		0.25	0.03		0.08	0.08			0.2		6			0.03	R			Y	Ø 40x13mm	RM	Disc														
341-SA4R	%			0.04		0.13	0.003		0.1	0.09			0.1		3.9			0.006	R				Ø 40x15mm	CRM	C Disc														
341-SA5R	%			0.03		0.003	0.019		0.008	0.007			0.035		5.3			0.001	R				Ø 40x15mm	CRM	C Disc														
341-SA6R	%			0.057		0.23	0.009		0.07	0.03			0.22		5.9			0.022	R				Ø 40x15mm	CRM	C Disc														
						TIN ALLOY						SnSbCuPb																											
		Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	S	Sb	Se	Tl	Zn	Sn		Others/Set Only	Size	Type	Alloy															
185-LA1	%			0.012		0.014	1.41		2.45	0.012		0.011	3.18		6.79			0.0016	R			Y	Ø40x25mm	CRM															
185-LA2	%		0.092			0.033	0.88		3.84	0.018		0.094	2.17		7.81				R			Y	Ø40x25mm	CRM															
185-LA3	%			0.24		0.059	0.5		8.13	0.059		0.28	1.19		10.22			0.0095	R			Y	Ø40x25mm	CRM															
185-LA4	%			0.43		0.085	0.096		6.35	0.08		0.45	0.41		11.66				R			Y	Ø40x25mm	RM															
185-LA5	%			0.54		0.099	0.011		5.45	0.096		0.53	0.07		13.58			0.021	R			Y	Ø40x25mm	CRM															

